

**AMENDMENT NO. 2 JULY 1992
TO
IS 4835 : 1979 SPECIFICATION FOR POLYVINYL
ACETATE DISPERSION BASED ADHESIVES FOR
WOOD**

(*First Revision*)

(*Pages 5 and 6, clauses 6.5.1 and 6.6, last sentence*) — Substitute the following for the existing last sentence :

‘For preparation of test pieces as required under Appendix F of IS 851 : 1978*, veneers of *canarium* spp. or *vateria indica* or *shorea assamica* shall be taken.’

(*Page 10, clause C-1.1*) — Substitute the following for the existing clause :

‘C-1.1 Test slips, 3.0 ± 0.2 mm thick, shall be prepared from *canarium* spp. or *vateria indica* or *shorea assamica*. Both faces of the slips shall be planed properly’

(*Page 10, clause C-3.1*) — Substitute the following for the existing clause:

‘Each test specimen 115 ± 0.25 mm long and 25 ± 0.3 mm wide shall be prepared from three slips of *canarium* spp. or *vateria indica* or *shorea assamica*, selected as described under C-1, joined together with the adhesives under test so as to produce a 12.5 ± 0.3 mm overlap joint as shown in Fig. 1.’

(CED 20)