

AMENDMENT NO. 2 JULY 2024
TO
IS 17730 (PART 1) : 2021 AGRO TEXTILES — HAIL PROTECTION NETS FOR
AGRICULTURE AND HORTICULTURE PURPOSES — SPECIFICATION
PART 1 WARP KNITTED HAIL PROTECTION NETS

(Page 1, clause 6.2) — Substitute the following for the existing:

‘A reinforcement of minimum 10 cm of 6 gauge shall be provided at both the selvedge ends for all widths of hail protection nets. For hail protection nets of width more than 6 m, reinforcement of minimum 10 cm of 6 gauge shall also be provided at the centre of the net.

NOTE — If agreed to between the buyer and the seller, a reinforcement of minimum 10 cm of 6 gauge may also be provided at the centre of the knitted hail protection nets of width less than 6 m.’

[Page 2, Table 1, Sl No. (viii), (see also Amendment No. 1)] — Substitute the following for the existing:

Sl No.	Characteristic(s)	Requirement(s)		Method of Test, Ref to
		Type 1	Type 2	
(1)	(2)	(3)	(4)	(5)
viii)	Seam (joint) strength ²⁾ , N, <i>Min</i> :			IS/ISO 13935-1
	a) Wales direction	155	155	
	b) Course direction	215	255	

[Page 2, Table 1, footnote, (see also Amendment No. 1)] — Insert the following new footnote at the end of the table:

‘²⁾ The seam strength testing shall be done in the applicable direction of stitching.’