

AMENDMENT NO. 2 JULY 2024
TO
IS 17730 (PART 2) : 2021 AGRO TEXTILES — HAIL PROTECTION NETS
FOR AGRICULTURE AND HORTICULTURE PURPOSES —
SPECIFICATION
PART 2 WOVEN HAIL PROTECTION NETS

(Page 1, clause 6.2) — Substitute the following for the existing:

‘A reinforcement of minimum 10 cm shall be provided at both the selvedge ends for all widths of hail protection nets. A reinforcement of minimum 10 cm shall also be provided at the centre of woven hail protection nets of width more than 6 m.

NOTE — If agreed to between the buyer and seller, a reinforcement of minimum 10 cm may also be provided at the centre of the woven hail protection nets of width less than 6 m.’

[Page 2, Table 1, Sl No. (ix), (see also Amendment No. 1)] — Substitute the following for the existing:

SI No.	Characteristic(s)	Requirement(s)		Method of Test, Ref to
		Type 1	Type 2	
(1)	(2)	(3)	(4)	(5)
ix)	Seam (joint) strength ²⁾ , N, Min:			IS/ISO 13935-1
	a) Warpway	385	385	
	b) Weftway	240	255	

[Page 2, Table 1, Sl No. (ix), (see also Amendment No. 1)] — Insert the following new footnote at the end of the table:

²⁾ The seam strength testing shall be done in the applicable direction of stitching.’