

AMENDMENT NO. 1 FEBRUARY 2025
TO
IS 18433 (PART 1) : 2023 MEASUREMENT OF SURFACE FRICTIONAL
PROPERTIES — METHODS OF TEST
PART 1 PENDULUM TEST

(Page 1, clause 2) — Insert the following in ascending order:

<i>‘IS No.</i>	<i>Title</i>
IS 3400 (Part 2/Sec 2) : 2023/ISO 48-2 : 2018	Methods of test for rubber, vulcanized or thermoplastic: Part 2 Determination of hardness Section 2 Hardness between 10 IRHD and 100 IRHD (<i>fifth revision</i>)
IS 3400 (Part 11) : 2021/ISO 4662 : 2017	Methods of test for vulcanized rubber: Part 11 Determination of rebound resilience (<i>second revision</i>)’.

(Page 2, clause 5.2, last sentence) — Delete.

(Page 2, clause 5.2) — Insert the following at the end:

‘For the rubber:

- a) The rebound resilience (measured) in accordance with IS 3400 (Part 11) shall be 21 percent to 26 percent; and
- b) International rubber hardness degree, measured in accordance of IS 3400 (Part 2/Sec 2) shall be 96 ± 2 IRHD.’

(Page 2, clause 6.2) — Insert the following at the end:

‘Laboratory temperature shall be maintained at $25\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ during the test.’