

AMENDMENT NO. 1 JANUARY 2026
TO
IS 18930 : 2024 TEXTILES — POLYESTER FIBRE FILLED PILLOW —
SPECIFICATION

(Page 1, clause 6.2) — Substitute the following for the existing:

‘The outer protective cover shall conform to the requirements as specified in Table 3 (optional).’

[Page 2, Table 1, Sl No. (v)] — Substitute the following for the existing:

Sl No.	Type	Fiber Type	Count of Yarn (for Guidance only)		Ends/cm	Picks/cm	Mass g/m ² , Min
			Warp	Weft			
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
v)	Tolerance	± 3 percent (see Note)	—	—	± 4	± 3	—

(Page 2, Table 1, Note) — Substitute the following for the existing:

‘NOTE — The tolerance specified under col (3), Sl No. (v) is applicable to the fibre blend composition of Type 4 casing fabric. The tolerances given under col (6) and col (7), Sl No. (v) are applicable to all casing types.’

[Page 2, Table 2, Sl No. (iii)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement				Method of Test, Ref to
		Type 1	Type 2	Type 3	Type 4	
(1)	(2)	(3)	(4)	(5)	(6)	(7)
iii)	Dimensional change (after 3 washes), (see Note) percent: a) Warp b) Weft	+ 3 to - 3		+ 3 to - 5		IS 15370/ISO 6330 Type A (6N) and ISO 5077

(Page 3, Table 2) — Insert the following at the end:

‘NOTE — Tumble drying shall be used for drying unless otherwise specified in care instructions on the wash care label.’

(Page 3, Table 3, title) — Substitute the following for the existing:

‘Table 3 Outer Protective Cover Requirements (Optional).’

[Page 3, Table 3, Sl No. (vi) and (vii)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
vi)	Dimensional change (after 3 washes), (see Note 2) percent: a) Warp b) Weft	+ 3 to - 3	IS 15370/ISO 6330 Type A (6N) and ISO 5077

Price Group 1

Amendment No. 1 to IS 18930 : 2024

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
vii)	General appearance after washing (<i>see</i> Note 3)	No seam opening or broken stitches, no delamination of TPU lamination	

(Page 3, Table 3, Notes) — Substitute the following for the existing:

‘NOTES

1 Colour fastness to saliva and perspiration is applicable for dyed fabric only.

2 For appearance after washing sample used in dimensional change after 3 washes to be evaluated visually.

3 Tumble drying shall be used for drying unless otherwise specified in care instructions on the wash care label.’

(Page 4, clause **6.3**) — Substitute the following for the existing:

‘6.3 Filler

The filling fibre shall be virgin hollow conjugate siliconized polyester fibre conforming to IS 17263. The nominal fibre denier of filler fibre may be either 15, 7, 4 or 3.’

(Page 4, Table 4) — Delete.

(Page 8, Annex A) — Insert the following references at the appropriate place:

<i>‘IS No./Other Standard</i>	<i>Title</i>
ISO 5077 : 2007	Textiles — Determination of dimensional change in washing and drying’