

AMENDMENT NO. 1 JULY 2025

TO

IS 19103 : 2025 COIR PITH BLOCK — SPECIFICATION

(Page 1, clause 1) — Substitute the following for the existing:

‘This standard prescribes the requirements of coir pith blocks made from dried and sieved coir pith extracted from coconut husk by mechanical means.’

(Page 1, clause 3.1.1) — Delete.

(Page 1, clause 3.1.2) — Delete.

(Page 1, clause 5.1) — Substitute the following for the existing:

‘5.1 Coir pith, which is also known as coir dust is the main byproduct from coir extraction industries. In the process of extraction of coir fiber from husk generally about one third of it is obtained as fiber and two third of it is obtained as coir pith. The process for the production of coir pith block follows a number of steps.’

(Page 2, clause 5.2) — Substitute the following for the existing:

‘5.2 Washing and Buffering of Coir Pith (Optional)

The coir pith is washed with water to further reduce the salt content. Buffering may also be done if agreed between the buyer and the seller. The pith can be buffered using the same process as washing by mixing a solutions of calcium nitrate and or magnesium nitrate with water as required, followed by a further washing step.’

(Page 2, clause 5.3.1) — Substitute the following for the existing:

‘5.3.1 The washed coir pith is then dried and subjected to sieving/mixing process. The resultant pith is fed into the compacting machine in which the pith is converted into blocks of different weight such as 650 g or 5 000 g.’

(Page 2, clause 6.3.1) — Substitute the following for the existing:

‘6.3.1 The dimensions of the pith block shall be measured using a steel rule with graduation up to 1 mm’

(Page 2, clause 6.3.2) — Substitute the following for the existing:

‘6.3.2 The weight of the coir pith block when measured using an electronic balance to the nearest 0.1 g shall be subjected to the tolerance given in Table 2 for coir pith blocks of weight 650 g and 5 000 g.’

(Page 4, clause 10.1.1) — Substitute the following for the existing:

‘10.1.1 Lot

Quantity of coir pith block manufactured under similar conditions, having same grade and weight and delivered to a buyer against one dispatch note shall constitute a lot.’

(Page 5, clause A-4.2) — Substitute the following for the existing:

‘A-4.2 After soaking the coir pith for 6 h, measure the conductivity of the sample with conductivity meter and note down the reading’

(Page 5, clause A-5) — Substitute the following for the existing:

‘Calculate the mean of the three observed readings.’

Price Group 1

Amendment No. 1 to IS 19103 : 2025

(Page 5, clause **B-1.1**) — Substitute the following for the existing:

‘B-1.1 pH Meter

Potentiometer equipped with a glass-calomel electrode system.’

(Page 5, clause **B-2**) — Substitute the following for the existing:

‘B-2 CABLIBRATION OF pH METER

Calibrate the pH meter using standard buffer solutions.’

(Page 5, clause **B-4.2**) — Substitute the following for the existing:

‘B-4.2 After soaking the coir pith for 60 min, measure the pH of the sample with pH meter and note down the reading’

(Page 5, clause **B-5.1**) — Substitute the following for the existing:

‘B-5.1 Calculate the mean of the three observed readings.’

(Page 5, clause **B-5.2**) — Delete.

(Page 6, clause **D-3.2**) — Substitute the following for the existing:

‘D-3.2 Calculate the sand content by the following formula:

$$\text{Sand content, percent} = \frac{w_2}{w_1} \times 100$$

where

W_1 = mass, in g, of conditioned test specimen; and

W_2 = mass, in, g of sand.’