

**AMENDMENT NO. 2 DECEMBER 1998
TO
IS 12838 : 1989 BLAZER CLOTH — SPECIFICATION**

(*Page 2, Table 1*) — Insert the following at the end of the table:

Sl No.	Characteristic	Requirements	Method of Test
(1)	(2)	(3)	(4)
xiii)	Seam slippage at 120 kg load	No seam opening	Annex C

(*Page 5*) — Insert the following as Annex C to the standard alter Annex B:

ANNEX C

(*Table 1*)

METHOD OF TEST FOR SEAM SLIPPAGE

C-1 PRINCIPLE

A strip of fabric is folded and stitched across its width. A weight is applied to the strip at right angles to the seam using grab-test jaws and the extent to which the seam opens is measured.

C-2 APPARATUS

C-2.1 Electrically operated, single-needle, lock-stitch sewing machine

C-2.2 Machine needles, throat-plate, feed-dog and sewing thread appropriate to the fabric to be tested.

C-2.3 Means for gradually applying weight of 0.25 kg, 8 kg or 12 kg to the specimens under test. The face of one jaw of each fabric-holding clamp shall measure 25 mm × 25 mm and that of the other jaw 25 mm by not less than 40 mm, with the longer dimension perpendicular to the direction of application of the load. The jaws shall be capable of holding the specimen without allowing it to slip and shall be designed so that they do not cut or otherwise weaken the specimen. The faces of the jaws shall preferably be smooth and flat, but engraved or corrugated faces may be used.

C-3 PREPARATION OF TEST SPECIMENS

C-3.1 Cutting of Test Specimens — Cut rectangular specimens of length approximately 180 mm and width 100 mm. Unless otherwise agreed by the parties concerned, cut five specimens with their long sides parallel to the warp

Amend No. 2 to IS 12838 : 1989

and five specimens with their long sides parallel to the weft of the fabric. Select them to be as representative as possible of the bulk. Wherever possible, no two specimens in any group of five should contain the same warp or weft threads.

Condition the test specimens to the standard atmosphere for testing textiles as given in IS 6359 : 1971 for not less than 18 h. Further preparation and testing of each specimen is carried out with removal from the standard atmosphere for testing textiles.

C-3.2 Choice of Sewing Thread, Size of Needle and Stitch Length

The fabric specimen shall be stitched with mercerized cotton machine-twist sewing thread with the appropriate count as given below:

<i>Sewing thread</i>		<i>Needle with approximate blade diameter</i>	<i>Stitch length</i>	<i>Stitches/inch (for uniformation only)</i>
Cotton count	Approximate resultant count in tex			
36/3	49	1.02	2.5	10

C-3.3 Adjustment of Sewing Machine

Insert the appropriate size needle and the corresponding throat-plate and teed-dog, and set the machine to give the appropriate stitch length for the fabric under test when 'sewing' a piece of fairly stiff paper with the needle of the machine unthreaded. Measure the spacing of the holes thus produced. When the stitch length has been adjusted insert a new needle of appropriate size to be used for seaming the test specimen.

Adjust the thread tension as follows:

Remove the lower thread bobbin still in the case from the machine, hold the thread issuing from the bobbin case so as to allow the case to run down the thread as it unwinds. Adjust the tension spring on the bobbin case so that the case runs down the thread at a slow, uniform speed. Replace the bobbin case in the machine and adjust the tension of the thread feed to the needle so that when a double thickness of the fabric under test is stitched the cross-over between the needle thread and the bobbin or shuttle thread is located midway between the upper and lower surfaces of the seam.

Amend No. 2 to IS 12838 : 1989

C-3.4 Preparation of Test Specimens

Fold the specimen in half by putting the two shorter edges together and stitch a seam parallel to and at a distance of 12 mm from the fold. Increase the speed of a sewing machine to the specified range as quickly as possible and maintain it with that range until the seam has been completed. Tie the threads at each end of the seam. Cut each specimen along the fold

C-4 TEST PROCEDURE

C-4.1 Set the clamps of the weight-application device at a distance of 75 mm apart, taking care that the clamps are properly aligned and parallel.

C-4.2 Secure the specimen symmetrically in the clamps with the seam midway between and parallel to the edges of the two clamps.

C-4.3 Gradually increase the axial load on the specimen to 12 kg. Two minutes after the application of the appropriate load, determine the width of the seam opening at its widest place; measure at right angles to the seam from the edge of the undistorted fabric on one side of the seam to the edge of the undistorted fabric on the other.

C-5 CALCULATION AND EXPRESSION OF RESULTS

For each group of warp or weft specimens, calculate to the nearest 0.5 mm the mean value of the measured seam opening both at the maximum load applied and after reduction of the load to 0.25 kg.

(TX 04)