

**AMENDMENT NO. 1 AUGUST 1997
TO
IS 13000 : 1990 SILICA-ASBESTOS-CEMENT FLAT
SHEETS — SPECIFICATION**

(*Page 1, clause 3.1, line 4*) — Insert 'or 43 grade ordinary Portland cement conforming to IS 8112 : 1989 or 53 grade ordinary Portland cement conforming to IS 12269 : 1987' after 'IS 269 : 1989'.

(*Page 1, clause 7.2*) — Substitute the following for existing clause:

'7.2 The nominal lengths and widths of silica-asbestos-cement flat sheets shall conform to the values specified in Table 2.

Table 2 Nominal Dimensions of Asbestos Cement Sheets

Length	Width	
	1 200	1 220
(1)	(2)	(3)
mm	mm	mm
600	x	—
610	—	x
1 200	x	—
1 220	—	x
1 800	x	—
1 830	—	x
2 400	x	—
2 440	—	x
3 000	x	—
3 050	—	x

NOTE — By mutual agreement between the purchaser and the manufacturer, the sheets may be supplied in dimensions other than those specified in 7.2.

(*Page 2, clause 8.2*) — Substitute the following for the existing clause:

'8.2 Thickness

Amend No. 1 to IS 13000 : 1990

Carry out three measurements at one end cover width at approximately 20 mm from the edge by means of a gauge having a flat anvil of not less than 19 mm diameter accurate to measure 0.1 mm. The average of the three measurements shall correspond to the nominal thickness and the tolerance specified in 7.1 and 7.3.'

(Page 2, Annex A) — Insert the following after '7639 : 1975 Methods of sampling of asbestos cement products':

'8112 : 1989 43 Grade ordinary Portland cement (*first revision*)'.

(Page 2, Annex A) — Insert the following at the end:

'12269 : 1987 53 Grade ordinary Portland cement'.

(CED 53)