

**AMENDMENT NO 1 AUGUST 2010
TO
IS 13054 : 1991 QUARTZITE/QUARTZ FOR THE
PRODUCTION OF FERRO ALLOYS — SPECIFICATION**

(Page 1, clause 4.2.2):

a) *Line 1* — Insert ‘cohesive index’ after the words ‘thermal stability’.

b) *Line 2* — Substitute ‘500 g’ for ‘200 g’.

(Page 1, clause 4.2.2) — Substitute ‘+20 mm’ for ‘+19 mm’ wherever appears in the para.

(Page 1, clause 4.2.3) — Substitute the following for the existing:

‘Mechanical strength/thermal stability index after heating and cooling, as in 4.2.2, is characterized by the proportion of +5 mm after tumbling (100 revolutions in 2.5 minutes). The tumbling test may be done in accordance with IS 6495 : 1984. The drum size shall be as per Fig. 1. Accordingly, quartzite shall satisfy the following.’

(Page 1, clause 6.2) — Add the following new clauses after 6.2:

‘6.3 Number of Tests

Conduct at least 2 tests on each sample and report the average. If the difference between the results obtained is more than 4 percent in absolute, then repeat the above tests in duplicate on second sample. Average of the four results (in case of repeat) shall be reported.

6.4 Precision and Bias

Repeatability

The precision of the test method is being investigated by a task group. At this time these values have not been determined.

Reproducibility

No precision statement (reproducibility) has been determined for this test method because of the impracticability of obtaining, transporting and handling representative splits of the material in the quantities that will be needed to establish the precision statement.

Amend No. 1 to IS 13054 : 1991

Bias

Lack of reference material precludes a bias statement.

FIG. 1 ROTARY HANNOVER DRUM FOR LAB USE

(MTD 13)

Reprography Unit, BIS, New Delhi, India