

**AMENDMENT NO. 1 MAY 2002
TO
IS 13101 : 1991 NATURAL RUBBER LATEX,
CREAMED, AMMONIA PRESERVED —
SPECIFICATION**

[*Page 2, Table 1, Sl.No. (i), (iii) and (iv), col 1 to 4*] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement	
		Type 1	Type 2
(1)	(2)	(3)	(4)
i)	Dry rubber content, percent by mass, <i>Max</i>	56.0	52.0
iii)	Total alkalinity as ammonia, percent by mass, <i>Min</i>	0.7	0.7
iv)	Mechanical stability time, seconds, <i>Min</i>	425	400

(PCD 14)