

AMENDMENT NO. 1 MARCH 2022

TO

IS 1848 (PART 2) : 2018 WRITING AND PRINTING PAPERS — SPECIFICATION

PART 2 AIR MAIL/MANIFOLD, CARTRIDGE DRAWING AND CARTRIDGE WHITE, DUPLICATING ABSORBENT AND DUPLICATING SEMI-ABSORBENT AND POSTER MACHINE GLAZED TYPES

(Fifth Revision)

[Page 2, clause 5.2 c)] — Substitute first sentence with the following:

‘Mass of 500 sheets including wrapping paper, in kg/ream or 250 sheets including wrapping paper, in kg/packet’.

(Page 3, Table 1) — Replace the existing table with the following:

Table 1 Requirements for Writing and Printing Papers

(Clauses 4.6, 4.7 and 6.2)

Sl No.	Characteristics	Requirements					Method of Test	
		Air mail/ manifold	Cartridge drawing	Cartridge, white	Duplicating absorbent/ Duplicating, semi-absorbent	Poster, machine glazed		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	
i	Tensile Index Nm/g <i>Min</i>	{ CD MD	20	20	17	17	17	IS 1060 (Part 5/Sec 6)
			30	30	25	25	25	
ii	Brightness ISO, Percent, <i>Min</i>		80	80	75	72	75	IS 1060 (Part 4/Sec 13)
iii	Opacity Percent, <i>Min</i>		80	80	80	85	-	IS/ISO 2471
iv	One Minute Cobb Test g/m ² , <i>Max Average</i>		25	25	25	25-70	25	IS 1060 (Part 5/Sec 4)
v	Number of Double Fold, <i>Min</i>	{ CD MD	-	10	-	-	-	IS 1060 (Part 6/Sec 3)
			-	15	-	-	-	
vi	Gloss Percent <i>Min</i>		-	-	-	-	18 (glazed side only)	IS 1060 (Part 5/Sec 12)
vii	Smoothness (Bendtsen) ml/ min <i>Max</i>		200	300	300	300	300	Cl.3 of IS 9894
viii	Tear Index mN.m2/g <i>Min</i>	{ CD MD	4.0	4.0	4.0	4.0	4.0	IS 1060 (Part 6/Sec 1)
			3.5	3.5	3.5	3.5	3.5	
NOTES:								
i) Requirement of brightness and gloss are applicable for white papers only.								
ii) Tensile index = (Breaking length × 0.009 8); Tear index = (Tear factor × 0.098)								
CD = Cross direction MD = Machine direction								