

AMENDMENT NO. 1 AUGUST 1993
TO
IS 1898 : 1990 TIMBER FOR
AIRCRAFT CONSTRUCTION IN CONVERTED
FORM (FINISHED FORM) — SPECIFICATION
(Second Revision)

(Page 1, clause 7.1) — Substitute the following for the existing clause:

‘7.1 The density of timber when determined by the method described in Annex A shall be not less than 440 kg/m^3 or more than 580 kg/m^3 at a moisture content of 15 percent. The value of density shall be increased or decreased with the moisture content at the rate of 4 kg/m^3 for each one percent increase or decrease in moisture content from 15 percent.’

[Page 2, Table 1, *Sl No. (ii) and col 7*] — Substitute ‘Fig. 1’ for ‘Fig. 19C’.

(Page 2, Note 1 under Table 1) — Substitute

‘20 mm × 20 mm × 80 mm’ for ‘25 mm × 25 mm × 100 mm’.

(Page 2, clause A-1.2, last line) — Substitute ‘Cubic centimeter’ for ‘cubic metre’.

(Page 2, clause A-1.3) — Substitute the following for the existing formula:

$$\text{Density} = \frac{W}{V} \times 10^3 \frac{\text{kg}}{\text{m}^3}$$

(CED 9)

Reprography Unit, BIS, New Delhi, India