

**AMENDMENT NO. 1 JANUARY 2012
TO
IS 1931 : 2000 ENGINEER'S FILES — SPECIFICATION**

(Third Revision)

(Page 3, clause 6, Title) — Substitute the following for the existing:

‘MATERIAL, HARDNESS AND MICROSTRUCTURE’

(Page 3, clause 6.2) — Insert the following new clause **6.3** below clause **6.2**:

‘6.3 Microstructure

The microstructure on the cutting portion of the file shall be uniformly distributed fine nodular carbides in martensitic matrix with no surface decarburization.’

(Page 3, clause 7.1.9) — Renumber clauses ‘7.1.9, 7.1.9.1, 7.1.9.2’ as ‘7.2.1, 7.2.1.1, 7.2.1.2’ and insert below clause **7.2** on page 12 of the standard and renumber the subsequent clauses.

[Page 10, Table 7, col 7, Sl. No. (ii)] — Substitute ‘17.5’ for ‘18.5’.

(Page 24, clause 8.1) — Substitute the following for the existing clause:

‘8.1 The tolerances on nominal length (*L*) shall be:

- a) Up to and including 300 mm ± 3.0 mm
- b) Over 300 mm ± 4.0 mm’

(Page 26, clause 13.3.1) — Substitute the following for the existing clause:

‘13.3.1 The hardness of hand prover for testing different files shall be as below:

- a) For saw files 635 to 675 HV or 57 to 59 HRC
- b) For engineers and mill files 580 to 615 HV *Min* or 54 to 56 HRC *Min*
- c) For other files 545 HV *Min* or 52 HRC *Min*’

(PGD 34)