

AMENDMENT NO. 1 JULY 2022
TO
IS 1969 (Part 1) : 2018 TEXTILES — TENSILE PROPERTIES OF FABRICS
PART 1 DETERMINATION OF MAXIMUM FORCE AND ELONGATION AT
MAXIMUM FORCE USING THE STRIP METHOD
(Fourth Revision)

(Foreword, para 6) — Insert the following new para after para 6:

‘This standard also permits the use of constant rate of traverse (CRT) machine for testing of jute fabrics including their laminates. Details of which are given in National Annex A.’

(Page 11, Annex B) — Insert the following National Annex A after Annex B:

‘NATIONAL ANNEX A
(Foreword)

For testing of jute fabrics including their laminates, the use of constant rate of traverse (CRT) machine is permitted. The rate of traverse shall be (450 ± 15) mm/min and gauge length shall be 200 mm.’

(TXD 01)

Publication Unit, BIS, New Delhi, India