

**AMENDMENT NO. 1 JUNE 1999
TO
IS 1992 : 1979 SPECIFICATION FOR
ELECTROPLATED COATINGS OF LEAD**

(First Revision)

(Page 4, clause 4.1.1) — Substitute the following for the existing clause:

‘4.4.1 Normally copper undercoat of 2.5 micron (Min), is required for all grades of lead plating.’

(Page 5, Table 1) — Substitute the following table for the existing:

Table 1 Thickness of Lead Plating

Grade	Designation	Thickness Min, Microns	Applications Area
4	FeCuPb40 or CuPb40	40	Accumulator fittings and other parts exposed to sulphuric acid and other industrial aggressive chemicals
3	FeCuPb25 or CuPb25	25	Outdoor exposures
2	FeCuPb12 or CuPb12	12	Mild outdoor exposures
1	FeCuPb6 or CuPb6	6	Indoor exposures

(Page 6, clause 8.2.1) — Substitute the following for the existing clause:

‘8.2.1 Stress Relieving Before Plating — Severely cold-worked steel parts made from steel of tensile strength of 980 MPa (100 kg/mm² or corresponding hardness of 30 HRC or 295 HV or 280 HB or above), which have been ground or subjected to severe machining after tempering, should normally be stress relieved at a temperature 190 ± 10°C for 5 h.’

(Page 6, foot-notes) — Delete the second footnote

(Page 9, clause B-4) — Substitute ‘ $\frac{M}{A} \times 8.882$ ’ for the existing.

(MTD 20)

Reprography Unit, BIS, New Delhi, India