

TO

**IS 2024 : 1988 SPECIFICATION FOR
FERROSILICOCHROMIUM**

(Third Revision)

(Page 1, Table 1, col 1, line 3) — Substitute the following for the existing grade:

Grade	Cr	Si	C, Max	Mn, Max	Al, Max	S, Max	P, Max
<i>Low Carbon</i>							
FeSi48Cr34	32-36	46-50	0.05	1.5	1.0	0.03	0.03

(Page 2, Table 3) — Substitute the following for the existing table:

Table 3 Particle Size Range

Size Designation	Size Range, mm		Over Size, Percent Max	Undersize, Percent Max	Remarks
	Over	Up to and Including			
1	100	315	10	15	No piece to exceed 1.15 times the maximum limit of size range specified in two of the three sides
2	25	100	10	15	
3	5	25	10	15	
4	—	5	10	—	

(MTD 5)