

AMENDMENT NO. 1 APRIL 2024

TO

**IS 2074 : 2023 READY MIXED PAINT, AIR DRYING, RED OXIDE — ZINC CHROME,
PRIMING — SPECIFICATION
(*Fourth Revision*)**

[Page 2, Table 1, *Sl No.* (i)] — Substitute the following for the existing *Sl No.* (i) in Table 1.

SI No.	Characteristic	Requirements	Methods of Test, Ref to	
			IS 101	Annex
(1)	(2)	(3)	(4)	(5)
i)	a) Consistency	Smooth, uniform and suitable for brushing without appreciable drag on the brush	—	C
	b) Viscosity by ford cup No. 4 at 27 °C ± 2 °C	80 s to 120 s	(Part I/Sec 5)	—

(CHD 20)