

**AMENDMENT NO. 1 MAY 2002
TO
IS 2076 : 1981 SPECIFICATION FOR UNSUPPORTED
FLEXIBLE POLYVINYL CHLORIDE SHEETING**

(First Revision)

(Page 7, clauses 6 and 6.1) — Substitute the following for the existing:

***6 CONDITIONING AND STORAGE**

6.1 Conditioning

6.1.1 For all test purpose minimum time between manufacture and testing shall be 16 h, in order to remove stresses and attain dimensional stability.

6.1.2 Sample shall be conditioned for 16 h minimum at standard atmosphere at a temperature of $27 \pm 2^{\circ}\text{C}$ and relative humidity 65 ± 5 percent before tests.

6.1.3 Unless otherwise specified, testing shall be carried out at $27 \pm 2^{\circ}\text{C}$ and relative humidity 65 ± 5 percent.

6.1.4 For product test, the time between manufacture and testing shall not exceed six months.

6.2 Storage

The roll of unsupported flexible polyvinyl chloride sheeting complying with this standard shall be stored vertically on dry, clean, firm level ground and at recommended temperatures in accordance with the manufacturer's instructions. The rolls shall be protected from dust, moisture, direct sunlight, corrosive and solvent fumes.'

(Page 10, clause B-1.1, Note) — Substitute the following for the existing:

'NOTE — It is recommended that the load scale/load cell be suitably calibrated atleast once every twelve months.'

(Page 18, clause E-2.3(c), line 1) — Substitute 'IS 2405 (Part 1):1980' for 'IS 2405:1963'.

(Page 18, footnote) — Substitute the following for the existing:

*Industrial sieves: Part 1 Wire cloth sieves (first revision) *

Amend NO. 1 to IS 2076 : 1981

(*Page 19, clause E-2.4, third para*) — Substitute 'IS 686 : 1985' for 'IS 686 : 1957*'

(*Page 19, footnote*) — Insert '(first revision)' at the end.

(PCD 12)