

AMENDMENT NO. 1 MARCH 1989
TO
IS : 2089 - 1977 SPECIFICATION FOR COMMON
PROOFED CANVAS/DUCK AND PAULINS
(TARPULINS)

(Second Revision)

(Page 4, clause 3.3.2.1, Note) — Substitute the following for the existing Note:

***NOTE** — Copper or zinc naphthenate are the only known economical and effective rot-proofing agents which do not leach out. The manufacturer shall provide evidence and make a declaration that he has used copper naphthenate conforming to IS : 1078-1987* and best trade quality zinc naphthenate. The purchaser, if he so desires, shall get copper naphthenate to be used, pre-tested conforming to IS : 1078-1987* before the manufacturer is permitted to use it. For this purpose, a proper record of pre-inspection of copper naphthenate shall be maintained by the manufacturer. Copper or zinc content when determined by the method prescribed in A-2, shall be *Min* 0.5 or 0.8 percent respectively when calculated on the mass of the proofing content. Manufacturer shall satisfy the buyer that the right quality and quantity of rot-proofing agent has been used, if necessary, by stage-control checks, proof of purchase and record of consumption of copper or zinc naphthenate. In case of doubt the buyer reserves the right to carry out biological appreciation as per IS : 1389-1984† before and after leaching as prescribed in this clause in addition to copper or zinc content determination as prescribed.*

*Specification for copper naphthenate (*second revision*).

†Methods for testing cotton fabrics for resistance to attack by micro-organisms (*first revision*).

(Page 7, clause 4.1.1.2, line 1) — Substitute 'rot-proofed cotton thread conforming to variety No. 18 or 43 of IS : 1720-1978* shall be used' for 'rot-proofed cotton thread conforming to variety No. 19 or 43 of IS : 1720-1969 shall be used'.

*Specification for cotton sewing threads (*second revision*).

(Page 7, clause 4.1.1.4) — Insert the following Note in the end:

***NOTE** — In case the length of 30 size eyelets conforming to IS : 4084-1978‡ is found to be inadequate for proper fixing of the fabric layers, eyelets of size higher than 30 given in IS : 4084-1978‡ may be used.*

‡Specification for eyelets and washers (*sail*) (*first revision*).

(Page 10, clause 4.2.5) — Insert the following after 4.2.5:

'4.2.5.1 For hook joints, number of stitches shall be between 16 to 20 per decimetre.'

(PCDC 16)