

**AMENDMENT NO. 2 FEBRUARY 2005
TO
IS 2089 : 1977 SPECIFICATION FOR
COMMON PROOFED CANVAS/DUCK AND PAULINS
(TARPAULINS)**

(Second Revision)

(Page 5, clause 3.3.7.1) — Substitute the following for the existing:

‘3.3.7.1 Pressure head test — A circular piece of common proofed canvas/duck 200 mm in diameter, when subjected to a constant pressure head of water in Table 2 for one hour according to method given in IS 7016 (Part 7) : 1986§ shall not show any leakage.

NOTE — In case small water drops (maximum 5 in different places) are found but these leakages stop during the test period, such defects should not be considered for rejection.’

(Page 5, footnote marked §) — Substitute the following footnote for the existing:

‘§ Method of test for coated and treated fabrics : Part 7 Determination of resistance to penetration by water (first revision).’