

AMENDMENT NO. 3 JANUARY 2008
TO
IS 101 (PART 8/SEC 2) : 1990 METHODS OF SAMPLING
AND TEST FOR PAINTS, VARNISHES
AND RELATED PRODUCTS
PART 8 TESTS FOR PIGMENTS AND OTHER SOLIDS
Section 2 Pigments and Non-Volatile Matter

(Third Revision)

(Cover page and page 1, Title) — Substitute ‘Section 2 Pigments, Non-Volatile Vehicle and Non-Volatile Matter’ for ‘Section 2 Pigments and Non-Volatile Matter’ and wherever it appears subsequently.

(Page 1, clause 4.5) — Add the following at the end:

‘4.6 Flat Bottom Dish, diameter 75 mm, made of glass or aluminium.

4.7 Hollow Glass Tube, 30 cm in length and 2 mm in diameter.’

(Page 2, clause 7.2.2) — Insert the following at the end:

‘7.3 Non-Volatile Matter Content

7.3.1 Take a petri dish of diameter (approximately 10 cm). Weigh it (w_1).

Now take about 2 g of paint sample and place it on the already weighed petri dish and immediately reweigh it (w_2).

Now spread it evenly by moving the Petri dish. Place it in an oven, already maintained at a temperature of $105 \pm 2^\circ\text{C}$ for 3 h.

The petri dish is removed, cooled and reweighed (w_3).

$$\text{Percent, NVC} = \frac{w_3 - w_1}{w_2 - w_1} \times 100$$

where

w_1 = mass, in g, of petri dish;

w_2 = mass, in g, of petri dish and paint sample before heating; and

w_3 = mass, in g, of petri dish and paint sample after heating.’

‘D 20)