

AMENDMENT NO. 1 APRIL 1982

TO

IS:207-1964 SPECIFICATION FOR GATE AND SHUTTER
HOOKS AND EYES

(Revised)

Alterations

(Page 4, clause 4.1) - Substitute the following
for the existing clause:

'4.1 Steel Wire - Mild Steel wire used in the manufacture of hooks and eyes shall conform to IS:1812-1973 Specification for Carbon Steel Wire for Manufacture of Wood Screws (first revision).'

(Page 4, clause 4.2.1, lines 2 and 3) - Substitute 'IS:3685-1966 Methods of Chemical Analysis of Brasses' for 'IS:441-1955 Method for Chemical Analysis of Brasses and Bronzes'.

(Page 5, clause 4.2.2) - Substitute the following
for the existing clause:

'4.2.2 Brass wire shall have a minimum ultimate tensile strength of 425 MPa ($\approx 42.5 \text{ kg/mm}^2$) and a minimum elongation at break of 15 percent, when tested in accordance with IS:2656-1964 Method for Tensile Testing of Copper and Copper Alloy Wire.'

(Page 5, clause 5.2, lines 2 and 3) - Substitute 'IS:451-1972 Technical Supply Conditions for Wood Screws (second revision)' for 'IS:451-1961 Specification for Wood Screws (revised)'.
'

(EDC 27)