

**AMENDMENT NO. 1 SEPTEMBER 1997
TO
IS 28 : 1985 SPECIFICATION FOR PHOSPHOR
BRONZE INGOTS AND CASTINGS**

(*Fourth Revision*)

(*Page 5, Table 1*) — Substitute the following for the existing table:

**Table 1 Chemical Composition
(*Clause 4.1*)**

Constituent	Percent				
	Grade 1	Grade 2	Grade 3	Grade 4	Grade 5
Copper	Remainder	Remainder	Remainder	Remainder	Remainder
Total impurities and alloying elements	1.20 <i>Max</i>	0.60 <i>Max</i>	0.50 <i>Max</i>	0.80 <i>Max</i>	0.20 <i>Max</i>
Alloying Elements					
Tin	6.0-8.0	10.0 <i>Min</i>	6.5-8.5	9.0-11.0	11.0-13.1
Phosphorus	0.30-0.50	0.50 <i>Min</i>	0.30 <i>Min</i>	—	0.15 <i>Min</i>
Lead	0.25 <i>Max</i>	—	2.0-5.0	—	0.50 <i>Max</i>
Zinc	—	—	2.0 <i>Max</i>	—	0.30 <i>Max</i>
Nickel	—	—	1.0 <i>Max</i>	—	0.50 <i>Max</i>
Iron	—	—	—	—	0.15 <i>Max</i>
Aluminium	—	—	—	—	0.01 <i>Max</i>
Impurities					
Phosphorus	—	—	—	0.15 <i>Max</i>	—
Lead	—	0.25 <i>Max</i>	—	0.25 <i>Max</i>	—
Zinc	0.50 <i>Max</i>	0.05 <i>Max</i>	—	0.05 <i>Max</i>	—
Nickel	0.70 <i>Max</i>	0.10 <i>Max</i>	—	0.25 <i>Max</i>	—
Iron	0.30 <i>Max</i>	0.10 <i>Max</i>	—	—	—
Aluminium	0.01 <i>Max</i>	0.01 <i>Max</i>	—	—	—
Antimony	0.10 <i>Max</i>	—	—	—	—
Silicon	0.02 <i>Max</i>	0.02 <i>Max</i>	—	—	0.02 <i>Max</i>

(MTD 8)