

AMENDMENT NO. 1 FEBRUARY 2015
TO
IS 299 : 2012 ALUMINO FERRIC — SPECIFICATION
(Fifth Revision)

(Page 1, clause **4.1**, line 8) — Substitute ‘pale yellow to light brown for Grade 4 and colourless to light yellow, clear liquid for Grade 5’ for ‘white to off-white for Grade 4 and almost colourless for Grade 5’.

[Page 2, Table 1, Sl No. (i), col 6] — Substitute ‘0.4’ for ‘0.2’.

[Page 2, Table 1, Sl No. (i), col 7] — Substitute ‘0.2’ for ‘0.1’.

[Page 2, Table 1, Sl No. (ii), col 2] — Substitute ‘Total soluble iron compound (as Fe^{2+} and Fe^{3+}), percent by mass, *Max*’ for ‘soluble iron compound (as Fe), percent by mass, *Max*’.

[Page 2, Table 1, Sl No. (ii), col 6] — Substitute ‘0.7’ for ‘0.04’.

[Page 2, Table 1, Sl No. (ii), col 7] — Substitute ‘0.35’ for ‘0.02’.

[Page 2, Table 1, Sl No. (v), col 2] — Substitute ‘Free acidity (as H_2SO_4)/ Basicity (as Al_2O_3), percent by mass, *Max*’ for ‘Free acidity (as H_2SO_4), Basicity (as Al_2O_3), percent by mass, *Max*’.