

AMENDMENT NO. 1 SEPTEMBER 2003
TO
IS 301 : 1982 SPECIFICATION FOR POTASSIUM
NITRATE FOR EXPLOSIVE AND PYROTECHNIC
COMPOSITIONS
(Second Revision)

(*Page 8, clause B-5.2*) – Substitute the following for the existing:

'B-5.2 Procedure — Weigh about 100 g of prepared sample and dissolve in adequate quantity of water. Heat, if necessary, cool and allow to settle. Decant the supernatant liquid carefully and dry the residue. Add 30 ml aqua regia, heat to boiling and boil for 10 min. Allow to cool and dilute with water. Filter through a tared filter paper, wash the residue with water free from chloride and dry at 105 to 110°C to constant mass.'

(CHD 26)