

AMENDMENT NO. 2 MAY 1983
TO
IS : 398 (Part III) - 1976 SPECIFICATION FOR
ALUMINIUM CONDUCTORS FOR OVERHEAD
TRANSMISSION PURPOSES

PART III ALUMINIUM CONDUCTORS, ALUMINIZED-STEEL
REINFORCED

(*Second Revision*)

Alterations

(*Page 12, clause 12.3*) — Substitute the following for the existing clause:

'12.3 Ductility Test — This test shall be made on aluminized ~~steel~~ wires only, by either of the two tests given in 12.3.1 and 12.3.2.'

(*Page 12, clause 12.3.2, Note*) — Substitute the following for the existing Note:

'NOTE - The choice between the torsion test and the elongation test shall be at the discretion of the purchaser. In the absence of any definite indication from the purchaser torsion test shall be carried out in preference to elongation test.'

(*Page 13, clause 13*) — Substitute the following for the existing clause:

'13. REJECTION AND RETESTS

13.1 Should any one of the test pieces selected fail to pass the tests, three further samples from the same batch shall be selected, one of which shall be from the length from which the original test sample was taken, unless that length has been withdrawn by the supplier.

13.2 Should all of the three test pieces from these additional samples satisfy the requirements of the tests, the batch represented by these samples shall be deemed to comply with the standard. Should the test pieces from any of the three additional samples fail, the batch represented shall be deemed not to comply with the standard.

Addenda

(**Page 5, clause 5.1**) - Add the following Note after the existing clause:

'NOTE — Lithium soap grease corresponding to Grade II of IS : 7623-1974* suitable for such application.

(*Page 5, clause 6.1*) — Add the following foot-note after the existing clause:

' * Specification for lithium soap greases.'

(ETDC 60)