

**AMENDMENT NO. 2 SEPTEMBER 2000**  
**TO**  
**IS 10646 : 1991 CANAL LININGS — CEMENT**  
**CONCRETE TILES — SPECIFICATION**  
**(First Revision)**

( *Page* 1, *clause* 2 ) — **Insert** of the following Indian Standard at the appropriate place:

‘456 : 1978      Code of practice for plain and reinforced concrete ( *third revision* )’

(*Page* 1, *clause* 3 ) — Insert the following at the end of the existing clause:

‘Concrete mix used in tile shall conform to M-15 grade specified in IS 456.’

(*Page* 1, *clause* 5 ) — **Substitute** the following for the existing clause:

‘Tolerance in length and breadth shall be  $\pm 3$  mm and thickness  $\pm 2.0$  mm.’

(*Page* 1, *clause* 7 ) — **Substitute** the following for the existing matter:

‘Samples for **flexural** shall be cured for 24 hours in shade and 21 days in water prior to testing. When tested according to the method given at Annex A, minimum breaking load per cm **weight** of the tile shall not be less than 41 kg for 60 mm, 29 kg for 50 mm and 18 kg for 40 mm **tiles** thickness.’

( WRD 13 )