

AMENDMENT NO. 2 OCTOBER 2025
TO
IS 10702 : 2023 HAWAI CHAPPAL — SPECIFICATION
(*Third Revision*)

[Page 1, clause 4, (see also Amendment No. 1)] — Substitute the following for the existing:

‘4 CATEGORY AND TYPE

The hawai chappal shall be of the following two categories based on their usage:

- a) For kids (standard English sizes for infants and children as per IS 1638 up to 220 mm last length); and
- b) For adults (All standard English sizes as per IS 1638 above 220 mm last length).

NOTE — This categorization is only for the purpose of differentiation between adults and kids and not for the purpose of defining sizes.’

[Page 2, Table 1, (see also Amendment No. 1)] — Insert the following at the end:

SI No.	Characteristic	Requirement			Method of Test, Ref to	
		For Kids ¹	For Adults		Annex	IS
			Type 1	Type 2		
(1)	(2)	(3)	(4)	(5)	(6)	(7)
ix)	Slip resistance, coefficient of friction (COF) ³ , <i>Min</i> (not applicable for leather sole) (to be carried out on quarry tiles)	—	0.3	—	—	Annex E of IS 15844 (Part 1)

[Page 3, Table 2, SI No. (iii), col (2), (see also Amendment No. 1)] — Add the following after the existing text:

‘(applicable for PVC only)’.

(Page 3, clause 5) — Delete.

(Page 9, clause C-2.6) — Substitute the following for the existing:

‘C-2.6 Rectangular or Square Specimen:

$$\text{Density (g/cm}^3\text{)} = \frac{1\,000 \times F}{T \times W \times L}$$

where

F = mass, in g, of the test specimen;

T = arithmetic mean of the five thickness readings, in mm;

W = arithmetic mean of the four width measurements; and

L = length, in mm, of the two shorter edges of the test specimen.’

Price Group 1

Amendment No. 2 to IS 10702 : 2023

(Page 9, clause C-2.7) — Substitute the following for the existing:

‘C-2.7 Circular Specimen

$$\text{Density (g/cm}^3\text{)} = \frac{F \times 4\,000}{3.14 [(D) \times (D) \times (T)]}$$

where

F = mass, in g, of the test specimen;

D = arithmetic mean of the three diameter readings in mm; and

T = arithmetic mean of the five thickness readings, in mm.’