



AMENDMENT NO. 1 DECEMBER 1986

TO

IS:10772-1983 SPECIFICATION FOR QUICK SETTING
LIME POZZOLANA MIXTURE

(Page 4, clause 3.1) - Substitute the following for the existing clause:

3.1 Quick setting lime pozzolana mixture shall be manufactured by intergrinding hydrated class C lime (see IS:712-1984[†]), pozzolana such as calcined clay (see IS:1344-1981[†]), flyash (see IS:3812-1981[†]) or rice husk ash, together with type IV gypsum (see IS:1290-1973^{II}), and/or suitable hardening accelerators in suitable proportions to comply with the requirements of this specification.

NOTE 1 - The lime reactivity value of pozzolanas when tested in accordance with the procedure given in IS:1727-1967^I shall not be less than 3.0 N/mm².

NOTE 2 - The gypsum content shall not exceed 5 percent by mass of lime and pozzolana content. When other types of accelerators are used such as metallic sulphates, chlorides, alum, metallic silicofluorides, silicates and carbonates, any particular accelerator shall not exceed 1 percent of lime and pozzolana content by mass.'

(Page 4, foot-note with '†' mark) - Substitute 'third revision' for 'second revision'.

(EDC 4)