

AMENDMENT NO. 1 MAY 1996
TO
IS 10774 : 1993 CORROSION RESISTANT HIGH ALLOY
STEEL AND NICKEL BASE INVESTMENT CASTINGS
FOR GENERAL APPLICATION — SPECIFICATION
(First Revision)

(*Page 1, clause 3.3*) — Substitute the following for the existing:

'3.3 Investment Casting

An investment casting is one that is produced in a mould shell obtained by investing (surrounding) an expendable pattern with a bonded refractory. The expendable pattern may be made of wax, urea, plastic or other material and is removed by heating or any other process prior to filling the mould with liquid metal.'

(*Page 2, clause 9.2*) — Substitute 'IS 11166 : 1993' for 'IS 11166 :1984'.

(*Page 3, clause 13.2*) — Substitute the following for the existing:

'13.2 The thickness or Dia of the As Cast Test Bar is ordinarily to be 18 ± 3 mm. However, size other than this may be agreed to between the manufacturer and the purchaser.'

(*Page 3, clause 13.2.1*) — Delete.

(*Page 4, Figures 1 and 2*) — Delete.

[*Page 4, clause 14.2(a)*] — Substitute 'IS 7666 : 1988' for 'IS 7666 : 1975'.

[*Page 5, clause 14.3 (d), line 2*] — Delete '(Under Print)'.

(MTD 17)