

AMENDMENT NO. 1 NOVEMBER 2010
TO
IS 10803 : 1984 METHOD OF SAMPLING AND PREPARATION OF WELD
PAD FOR CHEMICAL ANALYSIS OF WELD METAL FROM COVERED
ELECTRODES FOR MANUAL METAL ARC WELDING

(Page 4, clause 2.2) — Substitute the following for the existing:

Dimensions — The dimensions of the backing plate shall not be less than the following:

<i>Electrode Size, mm</i>	<i>Backing Plate Size, mm</i>
1.6, 2.0, 2.5, 3.15/3.2,	55 × 55 × 10-15 mm
4.0, 5.0, 6.3	65 × 65 × 10-15 mm

At least eight layers shall be deposited. The sampling will be done from at least 6.4 mm above original base metal:

<i>Electrode Size</i>	<i>Dimensions of Deposit, Min, mm</i>
1.6, 2.0, 2.5	30 × 30 × 13
3.15/3.2, 4.0, 5.0	40 × 40 × 16
6.30	40 × 40 × 20

(Page 5, clause 3.5.3) — Substitute the following for the existing:

‘Deposition should be carried out at a normal speed with minimum weaving. The width of each bead shall be 1.5 to 2.5 times the diameter of the core wire of the electrode, however, size of beads will vary according to the size of electrode and width of the weave.’

(Page 5, clause 3.5.5.4) — Add the following at the end:

‘The slag shall be removed after each pass.’

(MTD 11)