

**AMENDMENT NO. 1 JULY 2002
TO
IS 10810 (PART 33) : 1984 METHODS OF TEST FOR
CABLES
PART 33 WATER ABSORPTION TEST (GRAVIMETRIC)**

(Page 1, clause 6.1) — Substitute the following for the existing clause:

6.1 Slices of 0.6 to 0.9 mm thickness shall be ground or cut from the insulation or sheath with surfaces approximately parallel and free from roughness. Test pieces 80 to 100 mm long and 4 to 5 mm wide shall be punched out of the slices. Cut surfaces shall be smooth and care shall be taken not to overheat or otherwise to damage the specimen during the grinding/machining operation.'

(ET 09)

Reprography Unit. BIS, New Delhi, India