

AMENDMENT NO. 2 SEPTEMBER 2007
TO
IS 10810 (PART 33) : 1984 METHODS OF
TEST FOR CABLES

PART 33 WATER ABSORPTION TEST (GRAVIMETRIC)

(Page 1, clause 6.1) — Substitute the following by the existing clause:

'6.1(a) For cables with conductor of nominal cross sectional area equal to or less than 25 mm² and rated voltage up to and including 0.6/1 kV: Each test piece shall be a piece of core approximately 300 mm in length.

(b) *For all other cables:* Slices of 0.6 to 0.9 mm thickness shall be ground or cut from the insulation or sheath with surfaces approximately parallel and free from roughness. Test pieces 80 to 100 mm long and 4 to 5 mm wide shall be punched out of the slices. Cut surfaces shall be smooth and care shall be taken not to overheat or otherwise to damage the specimen during the grinding/machining operation.

(ET 09)

Reprography Unit, BIS, New Delhi, India