

AMENDMENT NO. 2 OCTOBER 1996
TO
IS 10840 : 1994 BLOW MOULDED HDPE CONTAINERS
FOR PACKING OF VANASPATHI — SPECIFICATION
(Second Revision)

(Page 1, clause 4.1.1, first para) — Substitute the following for the existing:

‘The material used for the container body shall be of HDPE of grade designation PE BAN A50 D003 or PE BAN A57 D003 or PE BAN A50 D006 or PE BAN A57 D006 or PE BAN A50 D001 conforming to IS 7328 : 1992.’

(Page 1, clause 4.1.2, line 3) — Substitute ‘D200’ for ‘T200’.

(Page 2, clause 4.3) — Substitute the following for the existing:

‘The minimum brimful capacity of the container when checked in accordance with the method given in Annex A shall be as under:

<i>Container Capacity</i>	<i>Minimum Brimful Capacity</i>
(kg)	(ml)
1	1 160
2	2 300
5	5 700
10	11 500
15	17 500

<i>Container Capacity</i>	<i>Minimum Brimful Capacity</i>
(litres)	(ml)
1	1 040
2	2 070
5	5 130
10	10 350
15	15 750

NOTE — The brimful capacity of the container may be calculated on the basis of the specific gravity of vanaspathi and may vary with the filling process and filling temperature. The purchaser of the container shall specify the brimful capacity according to the method and temperature of his filling.’

(PCD 21)

Reprography Unit, BIS, New Delhi, India