

AMENDMENT NO. 1 SEPTEMBER 1972
TO
IS : 2245-1962 METHODS OF SAMPLING
QUARTZITE

In order to make the procedure for sampling from wagons more economical and practical, the Methods of Sampling Sectional Committee, responsible for the preparation of this standard, decided to issue the following amendment.

Addendum

(*Page 8, clause 4.1.3*) — Add the following Note under this clause:

‘ *Note* — In the case of smaller lots of not more than 5 wagons, the unit samples/increments shall be collected from each of the wagons in the sub-lot according to the methods given in 4.1.2 or 4.1.3. However, in the case of larger lots of more than 5 wagons, at least 25 percent of the wagons, subject to a minimum of 5, shall be selected at random from the sub-lot and then the required number of unit samples/increments be evenly distributed over the selected wagons. ’

(SMDG 4)

Reproduced by Reprography Unit, ISI, New Delhi