

AMENDMENT NO. 3 NOVEMBER 2025
TO
IS 2347 : 2023 DOMESTIC PRESSURE COOKER — SPECIFICATION
(Seventh Revision)

(Page 3, clause 5.5) — Substitute the following for the existing:

‘The metallic part of PRD except the vent seal pin, shall be made of brass as per IS 319 or stainless steel of designation X02Cr18Ni11/X04Cr18Ni10/X07Cr18Ni9/X10Cr17Mn6Ni4 as per IS 6527 or stainless steel of designation X02Cr19Ni10/ X10Cr17Mn6Ni4N as per IS 6603 or stainless steel of properties conforming to Annex Q. The metallic part of PRD (sleeve) can also be made from heat insulating material like glass filled nylon (Nylon 6 or Nylon 66). In case of electric pressure cookers, the PRD shall conform to IS 302 (Part 1).

NOTES

- 1 Only chemical composition of stainless steel and brass needs to be complied with.
- 2 Supplier Certificate is acceptable in case of heat insulating material like glass filled nylon is used.’

(Page 5, clause 8.3.1) — Substitute the following for the existing:

‘The PRD shall operate within ± 20 percent of the nominal cooking steam pressure as declared by the manufacturer. The device shall pass the test prescribed in Annex G. Air pressure can be used for this test. The drop in the pressure after operation of the PRD shall not be more than 50 percent of the average measured cooking steam pressure when PRD operates (*see G-2*).’

(MED 33)

Price Group 1
Publication, BIS, New Delhi