

AMENDMENT NO. 1 SEPTEMBER 1980

TO

IS:2380(Parts I to XXI)-1977 METHODS OF TEST FOR
WOOD PARTICLE BOARDS AND BOARDS FROM OTHER
LIGNOCELLULOSIC MATERIALS

(First Revision)

PART I PREPARATION AND CONDITIONING OF TEST SPECIMENS

Alteration

(Pages 7 and 8, clause 2.3) - Substitute the following for the existing clause:

'2.3 Soaking of Specimens for Test - The specimens to be tested, if required to be soaked, shall be submerged horizontally in water at $27 \pm 2^\circ\text{C}$ for 24 hours before test and shall be tested immediately after removal from the water. The specimens shall be separated by at least 15 mm from each other and from the bottom and sides of the container. These shall be covered by 25 mm of water at the top. When it is desired to obtain the effect of complete saturation, the specimens may be soaked for such longer period as may be necessary. The duration of soaking and the amount of water absorbed shall be determined and recorded.'

PART XVII DETERMINATION OF SWELLING IN WATER

Alteration

(Page 55, clause 2.2.1) - Substitute the following for the existing clause:

'2.2.1 Each test specimen shall be immersed horizontally in fresh clean water having a temperature of

27 $\pm$ 2°C, the water being renewed for each test. The test specimens shall be separated by at least 15 mm from each other and from the bottom and sides of the container. These shall be covered by approximately 25 mm of water.'

(BDC-20)