

AMENDMENT NO. 2 MAY 1984
TO
IS : 2380 (Parts I to XXI) -1977 METHODS OF TEST
FOR WOOD PARTICLE BOARDS AND BOARDS
FROM OTHER LIGNOCELLULOSIC MATERIALS

(First Revision)

PART I PREPARATION AND CONDITIONING
OF TEST SPECIMENS

Alteration

[Page 7, clause 2.3 (see also Amendment No. 1)] — Substitute the following for the existing clause:

‘ **2.3 Soaking for Specimens for Test** — The specimens to be tested, if required to be soaked, shall be sealed by coating with wax or other suitable sealant material on all the four edges of the specimen and shall then be submerged horizontally under 25 mm fresh clean water maintained at a temperature of $27 \pm 2^{\circ}\text{C}$ for 24 hours before test and shall be tested immediately after removal from the water. The test specimen shall be separated by at least 15 mm from each other and from the bottom and sides of the container. When it is desired to obtain the effect of complete saturation, the specimen may be soaked for such longer period as may be necessary. The duration of soaking and the amount of water absorbed shall be determined and recorded. ’

PART XVI DETERMINATION OF WATER ABSORPTION

Alterations

(Page 53, clause 3.2, first sentence) — Substitute the following for the existing sentence:

‘ The specimen shall be sealed by coating with wax or other suitable sealant material on all the four edges of the specimen and shall then be submerged horizontally under 25 mm fresh clean water maintained at a temperature of $27 \pm 2^{\circ}\text{C}$ ’.

(*Page 54, clause 4.1, first sentence*) — Substitute the following for the existing sentence:

The amount of water absorbed shall be calculated from the increase in mass of the specimen during the submersion, and the water absorption shall be expressed as the percentage of mass based on the mass, after conditioning '.

PART XVII DETERMINATION OF SWELLING IN WATER

Alterations

[*Page 55, clause 2.2.1 (see also Amendment No. 1)*] — Substitute the following for the existing clause:

' **2.2.1** Each test specimen shall be sealed by coating with wax or other suitable sealant material on all the four edges of the specimen and shall then be submerged under 25 mm fresh clean water maintained at a temperature of $27 \pm 2^{\circ}\text{C}$, the water being renewed for each test. The short edges of the test specimens shall be vertical, with the measured edges lower most, and the test specimen shall be separated by at least 15 mm from each other and from the bottom and sides of the container. '

(*Page 55, clause 2.2.2, line 1*) — Substitute ' additional period of 22 hours ' for ' such other period as may be specified '.

(BDC 20)