

**AMENDMENT NO. 3 JANUARY 1993
TO
IS 2380 (Parts 1 TO 21) : 1977 METHODS OF TEST
FOR WOOD PARTICLE BOARDS AND BOARDS
FROM OTHER LIGNOCELLULOSIC MATERIALS**

(First Revision)

**PART I PREPARATION AND CONDITIONING OF TEST
SPECIMENS**

(Page 7, clause 2.1) — Substitute the following for the existing clause:

‘2.1 Size of Specimen — The required test specimens shall be cut to the specified size (*see* relevant methods of test). Each test piece shall be with all edges cut square to the surface. The dimensions of specimens, that is, length, width and thickness, shall be measured to an accuracy of 0.02 mm provided the dimension measured is less than or equal to 15 cm. In case the dimension is more than 15 cm, the accuracy shall be to nearest 0.5 mm.’

(Page 7, clause 2.2) — Substitute the following for the existing clause:

‘2.2 Conditioning — The test specimen shall be exposed to an atmosphere maintained at a relative humidity of 65 ± 5 percent and a temperature of $27 \pm 2^{\circ}\text{C}$ until their masses are constant.’

(Page 7, clauses 2.2.1 and 2.2.2) — Delete.

**PART III DETERMINATION OF MOISTURE CONTENT AND
DENSITY**

(Page 12, clause 3.2.2, line 2) — Substitute the words ‘to an accuracy given in 2.1 of IS 2380 (Part 1) : 1977[‡]’ for ‘to an accuracy of not less than ± 0.3 percent’.

(Page 12, foot-note) — Insert the following at the end:

[‡]Methods of test for wood particle boards and boards from other lignocellulosic materials:
Part 1 Preparation and conditioning of test specimens (*first revision*).

PART IV DETERMINATION OF STATIC BENDING STRENGTH (MODULUS OF RUPTURE AND MODULUS OF ELASTICITY IN BENDING)

(*Page 13, clause 1.1, Note*) — Delete 'or 2.2.1'.

(*Page 13, clause 2.1, lines 6 and 7*) — Substitute the words 'to the accuracy given in 2.1 of IS 2380 (Part 1) : 1977*' for 'to an accuracy of not less than ± 0.3 percent'.

PART V DETERMINATION OF TENSILE STRENGTH PERPENDICULAR TO SURFACE

(*Page 19, clause 2.1, line 2*) — Delete 'or 2.2.1'.

(*Page 19, clause 3.1, lines 6 and 7*) — Substitute the words 'to the accuracy given in 2.1 of IS 2380 (Part 1) : 1977*' for 'to an accuracy of not less than ± 0.3 percent'.

PART VI DETERMINATION OF TENSILE STRENGTH PARALLEL TO SURFACE

(*Page 23, clause 2.1, line 2*) — Delete 'or 2.2.1'.

(*Page 25, clause 3.1, line 2*) — Substitute the words 'to the accuracy given in 2.1 of IS 2380 (Part 1) : 1977*' for 'to the accuracy of not less than ± 0.3 percent'.

(*Page 25, foot-note*) — Insert the following foot-note at the end:

'*Methods of test for wood particle boards and boards from other lignocellulosic materials:
Part 1 Preparation and conditioning of test specimens (*first revision*).'

PART VIII COMPRESSION PARALLEL TO SURFACE TEST

(*Page 29, clause 2.1, line 8*) — Substitute '2.2' for '2'.

PART IX DETERMINATION OF RESISTANCE TO SHEAR IN PLANE OF THE BOARD

(*Page 31, clause 3.1, line 1*) — Substitute '2.2' for '2'.

PART XI SURFACE HARDNESS

(*Pages 39 to 41, clauses 2.1, 3.1 and 4.1, last line*) — Substitute the words 'to the accuracy given in 2.1 of IS 2380 (Part 1) : 1977†' for 'to an accuracy of not less than ± 0.3 percent'.

(*Page 39 to 41*) — Insert the following foot-note at the end:

†Methods of test for wood particle boards and boards from other lignocellulosic materials
Part 1 Preparation and conditioning of test specimens (*first revision*)

PART XIII LONG TIME LOADING BENDING TEST

(*Page 45, clause 2.1, line 5*) — Substitute '2.2' for '2'.

PART XVI DETERMINATION OF WATER ABSORPTION

(*Page 53, clause 2.1, line 2*) — Substitute '2.2' for '2.2.1'.

PART XVII DETERMINATION OF SWELLING IN WATER

(*Page 55, clause 2.1, line 2*) — Substitute '2.2' for '2.2.1'.

PART XVIII DETERMINATION OF MASS AND DIMENSIONAL CHANGES CAUSED BY MOISTURE CHANGES

(*Page 59, clause 2.1, line 2*) — Substitute '2.2' for '2.2.1'.

(CED 20)