

AMENDMENT NO. 4 NOVEMBER 1998
TO
IS 2380 (Parts 1 to 21) : 1977 METHODS OF TEST FOR
WOOD PARTICLE BOARDS AND BOARDS FROM
OTHER LIGNOCELLULOSIC MATERIALS
PART 16 DETERMINATION OF WATER ABSORPTION

(First Revision)

[*Page 53, clause 3.2, first sentence (see also Amendment No. 2)*] —
Substitute the following for the existing:

‘The specimen shall be submerged horizontally under 25 mm fresh clean water maintained at a temperature of $27 \pm 2^{\circ}\text{C}$, the water being renewed for each test.’

PART 17 DETERMINATION OF SWELLING IN WATER

[*Page 55, clause 2.2.1, (see also Amendments No. 1 and 2)*] — Substitute the following for the existing :

‘2.2.1 Each test specimen shall be submerged under 25 mm fresh clean water maintained at a temperature of $27 \pm 2^{\circ}\text{C}$, the water being renewed for each test. The short edges of the test specimens shall be vertical with the measured edges lower most, and the test specimen shall be separated by at least 15 mm from each other and from the bottom and sides of the container.’

(*Page 56, clause 3.1, line 2*) — Substitute ‘2’ for ‘3’.

(CED 20)