

AMENDMENT NO. 2 OCTOBER 1991
TO
IS 2386 (Part 1) : 1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE
PART 1 PARTICLE SIZE AND SHAPE

(*Page 12, Fig. 2*) — Substitute '40 to 31.5' for '40 to 25'.

(*Page 13, Table V, col 2, third entry*) — Substitute '31.5-mm' for '25-mm'.

(*Page 13, clause 4.4.3*) — Substitute the following for the existing clause :

'4.4.3 The number of pieces passing the appropriate gauge in each size fraction shall be counted separately. The total mass of each size fraction of the sample also shall be determined.'

(*Page 13, clause 4.5*) — Substitute the following for the existing clause:

"4.5 Calculation and Reporting of Results

4.5.1 The number of pieces passing the appropriate gauge in each fraction shall be calculated as a percentage of the total number of pieces in each sieve fraction (x) . The mass of total number of pieces in each sieve fraction shall then be calculated as a percentage of the total mass of the whole sample (y). The weighted percentage of the mass of pieces passing the appropriate gauge in each sieve fraction shall then be calculated by multiplying 'x' by 'y'.

4.5.2 The flakiness index shall be expressed as the sum of weighted percentages of the material passing the appropriate gauge in each sieve fraction. If required, the flakiness index for each sieve fraction may be reported as weighted percentage of the material passing the appropriate gauge.'