

AMENDMENT NO. 3 SEPTEMBER 1997
TO
IS 2386 (PART 1) : 1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE
PART 1 PARTICLE SIZE AND SHAPE
(To be read with Amendment No. 2)

(Page 12, Fig. 2) — Substitute '21.50' for '19.50'.

(Page 13, Table V, line 3, col 3) — Substitute '21.50' for '19.50'.

(Page 13, Table V, line 3, col 4) — Substitute '64.4' for '58.5'.

(Page 13, clause 4.5) — Substitute the following for the existing clause:

'4.5 Calculation and Reporting of Result

4.5.1 The mass of pieces passing the appropriate gauge in each sieve fraction shall be calculated as a percentage of mass of the total number of pieces in each fraction (x) . The mass of total number of pieces in each sieve shall then be calculated as a percentage of the total mass of the whole sample that is the sample which is retained on 6.3 mm sieve (y). The weighted percentage of the mass of the pieces passing the appropriate gauge in each sieve fraction shall then be calculated by multiplying ' x ' by ' y '.

(CED 53)