

AMENDMENT NO. 3 OCTOBER 1983
TO
IS : 2386 (Part IV) - 1963 METHODS OF
TEST FOR AGGREGATES FOR CONCRETE
PART IV MECHANICAL PROPERTIES

Alterations

(*Page 5, clause 2.2*) — Substitute the following for the existing clause:

‘2.2 Apparatus — The apparatus for the standard test shall consist of the following:

- a) An open-ended 150 mm cylindrical cell with appropriate base plate and plunger, metal measure and tamping rod conforming to IS : 9376-1979 Specification for apparatus for measuring aggregate crushing value and ten percent fines value;
- b) A balance of capacity 3 kg readable and accurate to one gram;
- c) IS sieve of sizes 12.5 mm, 10 mm and 2.36 mm; and
- d) A compression testing machine capable of applying a load of 40 tonnes in not more than 10 minutes at a uniform rate of loading. The machine may be used with or without a spherical seating.

(*Page 5, Table 1, Note*) — Substitute the following Note for the existing:

‘NOTE — About 6.5 kg of natural aggregates is required to provide two test samples for 15 cm cylinder and about 1 kg for 7.5 cm cylinder. For lightweight aggregates, the quantity will vary depending on the density of the aggregate.’

(*Page 6, Fig. 1*) — Delete.

(*Page 7, clause 2.3.2*) — Substitute the following for the existing clause:

‘2.3.2 The quantity of aggregate shall be such that the depth of material in the cylinder, after tamping as described in 2.3.3, shall be about 10 cm.’

(*Page 8, clause 2.6 Note 1, last sentence*) — Delete.

(*Page 8, clause 2.6 Note 2*) — Substitute the following Note for the existing:

‘ *Note 2 — Aggregates smaller than 10 mm* — In general the smaller sizes of aggregates will give a lower aggregate crushing value, but the relationship between the values obtained with different sizes will vary from one aggregates to another. The tests on smaller aggregates may be made either using the standard apparatus described in 2.2 or a smaller apparatus consisting of a 75 mm cylindrical cell with appropriate accessories conforming to IS : 9376-1979 Specification for apparatus for measuring aggregates crushing value and ten percent fines value. In case a smaller apparatus is used, the errors for the smaller sizes of aggregate tested in the smaller apparatus are compensated since the results obtained with the smaller apparatus have been found to be slightly higher than those with the standard apparatus.

The accessories for the smaller apparatus shall be a balance of capacity 500 g, readable and accurate to 0.2 g; IS sieves of appropriate sizes as given in Table 1; and a compression testing machine capable of applying a load of 10 tonnes in not more than 10 min at a uniform rate of loading. Further, in the test using the smaller apparatus, the depth of material in the 75 mm cylinder shall be about 50 mm and the total load applied in 10 min shall be 10 tonnes.’

(*Pages 8 and 9, clause 3.2*) — Substitute the following for the existing clause:

‘ **3.2 Apparatus** — The apparatus shall consist of the following:

- a) A 150 mm cylindrical cell with appropriate plunger and base plate, tamping rod and metal measure conforming to IS : 9376-1979 Specification for apparatus for measuring aggregate crushing value and ten percent fines value;
- b) A balance of capacity 3 kg, readable and accurate to one gram;
- c) IS sieves of sizes 12.5 mm, 10 mm and 2.36 mm;
- d) A compression testing machine capable of applying a load of 50 tonnes in not more than 10 minutes at a uniform rate of loading. The load may vary from 0.5 to 50 tonnes; and
- e) A means of measuring the reduction in the distance between the platens of the testing machine to the nearest one mm during the test (for example, a dial gauge).

(*Page 9, clause 3.3.2*) — Substitute the following for the existing clause:

‘ **3.3.2** The quantity of aggregate shall be such that the depth of material in the cylinder, after tamping as described in 3.3.2.1, shall be about 10 cm.’

[*Page 19, clause 5.3.4.1 (see also Amendment No. 2), third line*] — Substitute ‘ 30 to 33 rev/min ’ for ‘ 20 to 33 rev/min ’.

[*Page 19, clause 5.3.5 (see also Amendment No. 2)*] — Substitute the following for the existing clause:

‘ **5.3.5 Reporting of Results** — The difference between the original weight and the final weight of the test sample shall be expressed as a percentage

of the original weight of the test sample. The mean of two results shall be reported as the percentage of wear. '

(Pages 26, 27 and 28, clauses 7 to 7.6) — Delete.

Addendum

{ Page 7, clause 2.3.3 } — Add the following at the end of the clause:

'(see Note given in Table 1)'

{ BDC 2 }