

AMENDMENT NO. 1 FEBRUARY 1982

TO

IS:2386(Part VI)-1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE

Part VI MEASURING MORTAR MAKING PROPERTIES
OF FINE AGGREGATE

Alteration

[Page 8, clauses 7 and 7.1 (renumbered as 8 and 8.1)] - Substitute the following for the existing clauses:

'8. REPORTING OF RESULT

8.1 Calculate the average crushing strength of not less than three specimens containing untreated sand. Similarly calculate the average crushing strength of the corresponding number of specimens containing treated sand. Report the average crushing strength of specimens containing untreated sand as a percentage of the average crushing strength of the specimens containing treated sand.'

Addendum

(Page 4, clause 1.1) - Add the following new clauses after 1.1 and renumber the clauses '2 to 7' as '3 to 8':

"2. BASIS FOR COMPARISON

2.1 The fine aggregate shall be compared in mortar, as described in this method, with a sample of the same aggregate that has been washed in a 3 percent solution of sodium hydroxide followed by thorough rinsing in water. The treatment shall be repeated till the washed material produces a colour lighter than that of

the standard solution described in 6.2.2 of IS:2386(Part II)-1963 'Methods of test for aggregates for concrete : Part II Estimation of deleterious materials and organic impurities'. However, it shall be ensured that no fines are lost while washing with sodium hydroxide. The washed and rinsed aggregate shall be checked with a suitable indicator such as phenolphthalein or litmus to assure that all traces of sodium hydroxide are removed from the aggregate before being used for making control mortar."

(EDC 2)