

AMENDMENT NO. 2 OCTOBER 1991
TO
IS 2386 (Part 6) : 1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE

PART 6 MEASURING MORTAR MAKING PROPERTIES OF FINE
AGGREGATE

(*Page 4, clause 2.2*) — Substitute the following for the existing clause :
‘2.2 Tamping Bar — The tamping bar shall be made of non-absorbent, abrasion resistant, non-brittle material such as a rubber compound having a Shore A durometer hardness of 80 ± 10 or seasoned teak wood rendered non-absorbent by immersion for 15 minutes in paraffin at approximately 200°C and shall have a cross-section of 12.5×25 mm and a convenient length of 125 to 150 mm. The tamping face shall be flat and at right angles to the length of the bar.’

(*Page 4, clause 2.4*) — Substitute the following for the existing clause :
‘‘2.4 Moulds — These shall be 50 mm cube moulds and shall conform to the requirements laid down in IS 10036 : 1982 ‘Specification for moulds for use in tests of cement and concrete’.’

(*Page 5, clause 3.1, Note*) — Delete.

(*Page 5, clause 5.1, line 2*) — Substitute ‘50 mm’ for ‘7.06 cm’.

(CED 2)