

**AMENDMENT NO. 5 FEBRUARY 2009
TO
IS 15328 : 2003 UNPLASTICIZED NON-PRESSURE
POLYVINYL CHLORIDE (PVC-U) PIPES FOR USE IN
UNDERGROUND DRAINAGE AND SEWERAGE
SYSTEMS — SPECIFICATION**

(Page 1, clause 1, Scope, line 6) — Substitute '63 mm' for '110 mm'.

(Page 3, Table 1, col 1 to 6) — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Outside Diameter, d_n	Mean Outside Diameter, d_m		Outside Diameter at Any Point, d_s	
		Min	Max	Min	Max
(1)	(2)	(3)	(4)	(5)	(6)
i)	63	63.0	63.3	62.2	63.8
ii)	75	75.0	75.3	74.1	75.9
iii)	90	90.0	90.3	88.9	91.2

(Page 4, clause 8.3, line 2) — Substitute 'IS 12235 (Part 8/Sec 1)' for 'IS 12235 (Part 8)'.

(Page 5, Table 2) — Insert the following new values of 'Nominal Outside Diameter' and 'Wall Thickness, e ' before Nominal Outside Diameter, d_n of 110 mm:

Nominal Outside Diameter, d_n mm	Wall Thickness e , mm	
63	—	2.7 + 0.4 ¹⁾
75	—	2.8 + 0.5 ¹⁾
90	—	2.9 + 0.5 ¹⁾

¹⁾ Wall thicknesses in these cases are more than what is calculated as per SDR in order to meet the stiffness requirement.

Amend No. 5 to IS 15328 : 2003

(Page 6, Table 3, col 1 to 7) — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Diameter, d_n	Socket			Spigot End	
		d_{sm} Min	A Min	C Max	l_1 Min	$H^{(1)}$
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	63	63.3	23	18	40	4
ii)	75	75.3	25	20	45	5
iii)	90	90.3	28	23	55	5

[Page 6, Table 4 (see also Amendment No. 1), col 1 to 7] — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Diameter, d_n	Socket			Spigot End	
		d_{sm} Min	d_{sm} Max	l_2 Min	l_1 Min	$H^{(1)}$
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	63	63.1	63.3	38.0	45	4
ii)	75	75.1	75.3	43.5	50	5
iii)	90	90.1	90.3	51.0	60	5

(Page 8, Table 6, Note, last line) — Substitute the following for the existing:

' e_{min} - measured minimum wall thickness in millimetres of the free length of the test specimen.'

Amend No. 5 to IS 15328 : 2003

(Page 8, clause 12.3) — Substitute the following for the existing:

The colour of the marking shall be as follows:

<i>Class of Pipe</i>	<i>Colour</i>
SN 2	Blue
SN 4	Green
SN 8	Brown

(Page 12, Table 8, col 1 to 5) — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Outside Diameter of Pipes, d_n , mm	Mass of Falling Weight kg	Fall Height	
			m	N.m
(1)	(2)	(3)	(4)	(5)
i)	63	0.25	2	5
ii)	75	0.25	2	5
iii)	90	0.5	2	10

(Page 13, Table 9, col 1 to 3) — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Outside Diameter of Pipe, mm	Number of Equidistant Lines to be Drawn
(1)	(2)	(3)
i)	63	3
ii)	75	4
iii)	90	4

Amend No. 5 to IS 15328 : 2003

(Page 15, Table 11, col 1 to 3) — Insert the following new values in the beginning and renumber the existing SI Nos. accordingly:

SI No.	Nominal Diameter of Pipe, d_n , mm	Deflection Speed, mm/min
(1)	(2)	(3)
i)	$d_n \leq 100$	2 ± 0.4

(CED 50)

Reprography Unit, BIS, New Delhi, India