

AMENDMENT NO. 1 APRIL 2022

TO

IS 15392 : 2003 ALUMINIUM AND ALUMINIUM ALLOY BARE FOIL FOR FOOD PACKAGING — SPECIFICATION

(Page 1, clause 1, line 4) — Substitute ‘0.100 mm (100 μm)’ for ‘0.075 mm (75 μm)’.

(Page 1, clause 3.1, line 2) — Substitute ‘from’ for ‘over’.

(Page 1, clause 3.1, line 3) — Substitute ‘0.100 mm’ for ‘0.075 mm’.

(Page 2, clause 10, Table 2) — Insert the following new preferred thickness:

SI No.	Nominal Thickness		Nominal Covering Area (m^2/kg)
	(mm)	(μm)	
(1)	(2)	(3)	(4)
xviii)	0.080	80	4.65
xix)	0.090	90	4.13
xx)	0.100	100	3.72

(Page 2, clause 13.1, Table 5) — Insert the following new Tensile Breaking Loads:

SI No.	Nominal Thickness		Breaking Load, Kg/cm of width
	(mm)	(μm)	Min
(1)	(2)	(3)	(4)
xviii)	0.080	80	3.63
xix)	0.090	90	4.09
xx)	0.100	100	4.54