

AMENDMENT NO. 2 JUNE 2026
TO
IS 15462 : 2019 POLYMER MODIFIED BITUMEN (PMB) — SPECIFICATION
(First Revision)

[Page 3, Table 1, Sl No. (A)(iv)] — Substitute the row for the existing.

‘Sl No.	Characteristics	Grades and Requirements					Method of Test, Ref to	
		PMB 64-10	PMB 70-10	PMB 76-10	PMB 82-10	PMB 76-22	Annex	IS/ASTM
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
(iv)	Viscosity at 150 °C, Pa.s, Max	1.2	1.2	1.4	1.7	1.6	—	ASTM D 4402

[Page 3, Table 1, Sl No. (B)(iii)(d), col (2)] — Delete ‘J_{nrdiff}, Max 75 percent’.