

AMENDMENT NO. 2 DECEMBER 2025
TO
IS 15477 : 2019 ADHESIVES FOR USE WITH CERAMIC, MOSAIC AND
STONE TILES — SPECIFICATION
(First Revision)

[Page 5, clause A-6, (a)] — Substitute the following for the existing:

‘a) *Dry condition:*

- 1) Store the specimens under standard conditions for 27 days;
- 2) Thereafter bond the pull head plates to the tiles with a suitable high strength adhesive (*Example, Epoxy*);
- 3) Thereafter store them for further 24 h under standard conditions; and
- 4) Determine the tensile adhesion strength of the adhesive as per the procedure given in A-7.’

[Page 5, clause A-6, (b)] — Substitute the following with the existing:

‘b) *Wet condition:*

- 1) Store the specimens under standard conditions for 7 days;
- 2) Thereafter immerse in water at standard temperature for 20 days;
- 3) Remove the specimens from water, wipe the surface with a cloth, and let it dry for 30 to 45 minutes under standard conditions;
- 4) Bond the pull head plates to the tile or stone;
- 5) Keep the bonded sample for 7 h under standard conditions;
- 6) Subsequently, immerse the specimen in water for another 24 h at standard temperature; and
- 7) On the following day, that is, after a total of 28 days, remove the specimens from water, wipe the surface with a cloth and immediately determine the tensile adhesion strength of the adhesive as per the procedure given in A-7.’

(CED 05)

Price Group 1
Publication, BIS, New Delhi