

AMENDMENT NO. 2 MAY 2013
TO
IS 10918 : 1984 SPECIFICATION FOR VENTED TYPE
NICKEL CADMIUM BATTERIES

(Page 10, clause **10.7.5**) — Substitute ‘The capacity obtained in any one of the first five cycles shall not be less than 100 percent of the rated capacity specified by the manufacturer. The test to be concluded at the end of any of the stipulated five cycles which meets the above mentioned requirement.’ *for* ‘The capacity obtained in any of the first five cycles shall not be less than 95 percent of the rated capacity specified by the manufacturer.’

(Page 12, clause **10.12.2**, line 8) — Substitute ‘The capacity obtained in any one of the first five cycles shall not to be less than C_5 ’ *for* ‘The capacity obtained in any one of the first five cycles shall not to be less than $0.95 C_5$.’

(Page 12, clause **10.12.2**) — Insert the following new clauses:

‘10.13 Ampere-Hour and Watt-Hour Efficiency Tests

10.13.1 The test shall be conducted on a cell/battery which has qualified the capacity test when conducted according to **10.7**.

10.13.2 The test shall be conducted on cell/battery which is fully charged in accordance with **9.1**.

10.13.3 Discharge the cell at $0.2C_5$ current to a final voltage of 1.0 V/cell. The discharged ampere-hour to be calculated from the discharge duration (C_d). The cell is then recharged with the same ampere-hour input (C_d) at a current same as the previous discharge current ($0.2C_5$). The cell/battery is then again discharged at the same current ($0.2C_5$) to a final voltage of 1.0 V/cell. The ampere-hour output is again carefully calculated for this second discharge from the discharge duration (C_s). The efficiency of the cell is then calculated as the ratio of the ampere-hour delivered during the second discharge to the ampere-hour put in during the intermediate charge.

Amendment No. 2 to IS 10918 : 1984

10.13.4 The watt-hour efficiency shall be calculated by multiplying the ampere-hour efficiency with the ratio of the average discharge and recharge voltages. The average values of the voltages are calculated from the log sheets of the ampere-hour efficiency test.

10.13.5 Requirement

When measured in accordance to the above test procedure, the ampere-hour efficiency of the cell/battery shall not be less than 85 percent and the watt-hour efficiency shall not be less than 70 percent.'